



**Thermodyn™**  
*Where Your Success Is Sealed*

## **65 Duro White FDA Viton™ “A” Fluoroelastomer**

Product Code: TD-65-FDA  
Description: 66% Fluorine, food grade, genuine virgin Viton™ A fluoroelastomer  
Specifications: FDA Food Grade Compliant  
21 CFR 177.2600  
Temperature range -20°F-400°F

<u>Typical Rubber Properties</u>	<u>Test Method</u>	<u>Typical Value</u>
Hardness (Shore A)	ASTM D2240	65±5
Tensile Strength	ASTM D412	1500 psi min
Elongation	ASTM D412	200% min
Compression Set	ASTM D395B	23% max
Specific Gravity	ASTM D792	2.0 nominal
Color	Visual	Off-White

- Thickness & Width as specified.
- Material is available in black; however minimum purchase is 1 full roll.
- This is a specification grade of Viton™ -Type “A” fluoroelastomer recommended for use in aggressive media.
- This gasket is based upon only 100% Virgin Chemours Viton™ fluoroelastomer with 66% fluorine. No substitutions will be accepted.

Virgin Viton™ fluoroelastomer is defined as polymer supplied by The Chemours Company, and processed by a licensed Chemours Company Viton™ manufacturer, no scrap, re-grind, or re-processed fluoroelastomer compound shall be added to it.

Viton™ is a registered trade name of The Chemours Company



**THERMODYN CORPORATION**  
3550 Silica Road, Sylvania Ohio 43560 U.S.A.  
Phone: 419-841-7782 Toll-Free: 1-800-654-6518 (North America only) Fax: 419-841-3139  
[www.Thermodyn.com](http://www.Thermodyn.com)

